



RATNATECH

STAHL PVT LTD

Product Catalogue

Manufacturer & Exporter of Stainless Steel
Welded & Seamless Pipes | Tubes | U - Tubes



RATNATECH
STAHL PVT LTD

#RELIABLE RESILIENCE

Company Profile

Ratnatech is an ISO 9001:2015 Certified co. introduced as highly commended manufacturer and exporter of metal products in form of Seamless, Welded Pipes, Tubes & U-Tubes in Stainless Steel, Duplex, Super Duplex, Titanium Alloys, Aerospace Alloys & Special Alloys. Ensuring the finest products for our clients with modern production facilities including Cold Pilgering Mills, Tube mills with Plasma Welding, Draw Benches, Heat Treatment Solution & Bright Annealing Furnaces, U-Bending facilities and many more ancillary machinery and testing equipments to produce high quality tubes and pipes confirming to various international standards.

Our facilities are capable of manufacturing tubular products in martensitic, ferritic, austenitic, duplex /

super duplex and high nickel alloys grades. Here, tubes and pipes produced and supplied according to appropriate standards as well as customer specifications in good variety of steel grades and dimensions. **Ratnatech's** manufacturing programme consists of outside diameter of 3.00mm to 323.90mm with wall thickness of 0.50mm to 5.00mm, with specific requirements on execution, tolerances, lengths, mechanical and corrosion properties offered on request.

Ratnatech has a strong infrastructure and highly qualified, skilled and experienced engineers who contribute towards the company's growth and strives to produce best quality products in professionally managed work culture. We also conduct regular in-house as well as external training programme for our team to keep pace with ever changing technology.

Vision

To be the first choice of our customers by providing world class Pipes & Tubes.

Mission

Aspire to be a global organisation for tubular solutions based on transparency, structured systems that can encourage our business partners and employees to be with us for mutual growth.

Plant

Situated at Rajpur, Gujarat (Ahmedabad-Mehsana Highway) in radius of 45km north of Ahmedabad with 328000 sq ft. plot area manufacturing facility.



Products

Stainless Steel High Precision & Heat Exchanger Tubes

Outside Diameter	3.00 mm to 101.60 mm
Wall Thickness	0.50 mm to 10.00 mm
Length	Size Up to 30 Meter Long
U-Tubes	0.50 mm to 10.00 mm
Grades	304/L/H/LN, 316/L/H/LN/Ti, 309, 310/L/H/S, 317/L/H, 321/H, 347/H, 405, 409/L, 410, 430/Ti, 436, 439, 1.4301, 1.4306, 1.4571, 1.4541, 1.4401, 1.4404 UNS S31500, UNS S31803, UNS S2205, UNS S32750, UNS S32760
Specifications	Seamless – ASTM A-213, A-268, A-269, A-270, A-789, EN 10216-5 Welded – ASTM A-249, A-268, A-269, A-270, A-554, A-688, A-789, A-803, EN-10217-7
Supply Condition	Solution-Annealed, Pickled & Passivated Bright Annealed
Application	Heat Exchangers • Pressure Vessels • Chemical & Fertilizer • Marine Equipments • Refinery & Petrochemical • Process Industry • Dairy / Pharmaceutical Industry • Nuclear Power Generation • Automotive • Aerospace

Contact sales for more available grades

* Specifications as per ASTM, ASME, DIN, JIS (JAPAN), EN, NF(ANOR) also available



Stainless Steel Hydraulic & Instrumentation Tubes

Outside Diameter	3.00 mm to 15.87 mm
Wall Thickness	0.50 mm to 8.00 mm
Length	Length Upto 35 Meter Long, and 100 Meter for Small Diameter in Coil Form
Grades	304/L/H/LN, 316/L/H/LN/Ti, 309, 310/L/H/S, 317/L/H, 321/H, 347/H, 405, 409/L, 410, 430/Ti, 436, 439, 1.4301, 1.4306, 1.4571, 1.4541, 1.4401, 1.4404 UNS S31500, UNS S31803, UNS S2205, UNS S32750, UNS S32760
Specifications	ASTM A-213, A-269, A-789, EN 10216-5
Supply Condition	Solution-Annealed, Pickled & Passivated Bright Annealed
Application	Nuclear & Thermal Power generation · Oil & Gas · Process Industries · Chemical & Fertilizer · Nuclear Power · Food & Beverage Processing · Automotive · Aerospace · Medical & Pharmaceutical

Stainless Steel Seamless Pipes

Outside Diameter	1/8" NB to 12" NB
Wall Thickness	SCH 5S to SCH XXS
Length	As per Requirement. Maximum up to 24 Meter long
Grades	304/L/H/LN, 316/L/H/LN/Ti, 309, 310/L/H/S, 317/L/H, 321/H, 347/H, UNS S31500, UNS S31803, UNS S2205, UNS S32750, UNS S32760
Specifications	ASTM A-312, A-790
Supply Condition	Solution-Annealed, pickled and passivated. Can be supplied in other conditions on requirement.
Application	Onshore and Offshore Oil and Gas Production, Exploration and Transport (OCTG – Oil Country Tubular Goods) · Chemical & Petrochemical · Energy & Power Generation · Mechanical & Plant Engineering · Marine Equipment's · Pulp & Paper · Pharmaceutical Industry

Contact sales for more available grades

* Specifications as per ASTM, ASME, DIN, JIS (JAPAN), EN, NF(ANOR) also available



Stainless Steel Welded Pipes

Outside Diameter	1/8" NB to 12" NB
Wall Thickness	SCH 5S to SCH 80S
Length	As per Requirement. Maximum up to 35 Meter long
Grades	304/L/H/LN, 316/L/H/LN/Ti, 309, 310/L/H/S, 317/L/H, 321/H, 347/H, UNS S31500, UNS S31803, UNS S2205, UNS S32750, UNS S32760
Specifications	ASTM A-213, A-269, A-789, EN 10216-5
Supply Condition	Solution-Annealed, pickled and passivated. Can be supplied in other conditions on requirement.
Application	Chemical & Petrochemical · Gas Industry · Power Generation · Mechanical & Plant Engineering · Marine Equipment's · Pulp & Paper · Pharmaceutical Industry

Stainless Steel Box Pipes

Square	15×15 mm to 100×100 mm
Rectangular	15×30 mm to 100×50 mm
Wall Thickness Range	1.0 mm to 6.0 mm
Length	As per Requirement. Maximum up to 12 Meter long
Grades	As per Requirement.
Specification	As per Requirement.
Supply Condition	Annealed, pickled and passivated. Can be supplied polished condition on requirement.



Applications

Heat Exchangers

Refineries

Power Plant

Pharmaceuticals

Oil & Gas

Chemicals


Aerospace

Automobiles

Food Processing

Paper Pulp

Construction



Chemical Composition Of Stainless Steel

ASTM GRADE	UNS GRADE	DIN EN GRADE	STEEL NAME	JIS GRADE	C	Mn	P	S
TP 304	S30400				0.030	8.0-11.0	18.0-20.0	18.0-20.0
					0.030	8.0-11.0	18.0-20.0	18.0-20.0
					0.030	8.0-11.0	18.0-20.0	18.0-20.0
TP 304 L	S30403				0.030	8.0-11.0	18.0-20.0	18.0-20.0
					0.030	8.0-11.0	18.0-20.0	18.0-20.0
					0.030	8.0-11.0	18.0-20.0	18.0-20.0
TP309S	0.08				0.030	8.0-11.0	18.0-20.0	18.0-20.0
					0.030	8.0-11.0	18.0-20.0	18.0-20.0
					0.030	8.0-11.0	18.0-20.0	18.0-20.0
TP 317	0.08				0.030	8.0-11.0	18.0-20.0	18.0-20.0
					0.030	8.0-11.0	18.0-20.0	18.0-20.0
					0.030	8.0-11.0	18.0-20.0	18.0-20.0
TP 317L	0.08				0.030	8.0-11.0	18.0-20.0	18.0-20.0
					0.030	8.0-11.0	18.0-20.0	18.0-20.0
					0.030	8.0-11.0	18.0-20.0	18.0-20.0
TP 409	0.08				0.080	2.00	0.045	0.030
					0.070	2.00	0.040	0.015
					0.080	2.00	0.040	0.030
TP 904L	0.08				0.035	2.00	0.045	0.030
					0.030	2.00	0.040	0.015
					0.030	2.00	0.040	0.030
1.4462	0.08				0.04-0.10	2.00	0.045	0.030
					0.04-0.08	2.00	0.035	0.015
				SUS304HTB	0.04-0.10	2.00	0.040	0.030
TP 310S	S31008				0.080	2.00	0.045	0.030
		1.4845	X8CrNi25-21		0.100	2.00	0.045	0.015
				SUS310STB	0.080	2.00	0.040	0.030
TP 310H	S31009				0.04-0.10	2.00	0.045	0.030
		1.4335	X1CrNi25-21		0.020	2.00	0.025	0.010
TP 316	S31500				0.080	2.00	0.045	0.030
		1.4401	X5CrNiMo17-12-2		0.070	2.00	0.040	0.015
				SUS316TB	0.080	2.00	0.040	0.030
TP 316L	S31603				0.035	2.00	0.045	0.030
		1.4404	X2CrNiMo17-12-2		0.030	2.00	0.040	0.015
				SUS316LTB	0.030	2.00	0.040	0.030
TP 316H	S31609				0.04-0.10	2.00	0.045	0.030
		1.4918	X6CrNiMo17-13-2		0.04-0.08	2.00	0.035	0.015
				SUS316HTB	0.04-0.10	2.00	0.030	0.030
TP 316 Ti	S31635				0.080	2.00	0.045	0.030
		1.4571	X6CrNiMoTi17-12-2		0.080	2.00	0.040	0.015
				SUS316TiTB	0.080	2.00	0.040	0.030
TP 321	S32100				0.080	2.00	0.045	0.030
		1.4541	X6CrNiTi18-10		0.080	2.00	0.040	0.015
TP 321H	S32109				0.080	2.00	0.040	0.030
		1.4941	X5CrNiTiB18-10		0.04-0.10	2.00	0.045	0.030
				SUS321HTB	0.04-0.08	2.00	0.035	0.015
TP 347	S34700				0.04-0.10	2.00	0.030	0.030
		1.455	X5CrNiNb18-10		0.080	2.00	0.045	0.030
				SUS347TB	0.080	2.00	0.040	0.015
TP 347H	S34709				0.080	2.00	0.040	0.030
		1.4912	X7CrNiNb18-10		0.04-0.10	2.00	0.045	0.030
				SUS347HTB	0.04-0.10	2.00	0.040	0.015
TP 405	S40500				0.04-0.10	2.00	0.030	0.030
		1.4002	X6CrAl13		0.080	1.00	0.040	0.030
TP 410	S41000				0.080	1.00	0.040	0.015
		1.4006	X12Cr13	0.045	0.150	1.00	0.040	0.030
TP 430	S43000				0.045	0.018-0.15	1.50	0.015
		1.4016	X6Cr17	0.045	0.120	1.00	0.040	0.030
	UNS S31803				0.045	0.080	1.00	0.015
2205	UNS S32205				0.045	0.030	2.00	0.020
		1.4452	X2CrNiMoN22-5-3	0.045	0.030	2.00	0.030	0.020
2507	UNS S32750				0.045	0.030	2.00	0.015
		1.441	X2CrNiMoN25-7-4	0.045	0.030	1.20	0.030	0.020
	UNS S32760				0.045	0.030	2.00	0.015
		1.4501	X2CrNiMoCuWN25-7-4	0.045	0.050	1.00	0.030	0.010

Si	Cr	Ni	Mo	N	Nb	Ti	Cu	Al	W	B
1.00	18.0-20.0	8.00-11.0								
1.00	17.0-19.5	8.00-10.5		0.10 Max						
1.00	18.0-20.0	8.00-11.0								
1.00	18.0-20.0	8.00-12.0								
1.00	17.5-19.5	8.00-10.0		0.10 Max						
1.00	18.0-20.0	9.00-13.0								
1.00	18.0-20.0	8.00-11.0								
1.00	17.0-19.0	8.00-11.0								
0.75	18.0-20.0	8.00-11.0								
1.00	24.0-26.0	19.00-22.0								
1.50	24.0-26.0	19.00-22.0		0.11 Max						
1.50	24.0-26.0	19.00-22.0								
1.00	24.0-26.0	19.00-22.0								
0.25	24.0-26.0	20.00-22.0	0.20 Max.							
1.00	16.0-18.0	11.00-14.0	2.00-3.0							
1.00	16.5-18.5	10.00-13.0	2.00-2.5	0.10 Max						
1.00	16.0-18.0	10.00-14.0	2.00-3.0							
1.00	16.0-18.0	10.00-14.0	2.00-3.0							
1.00	16.5-18.5	11.00-13.0	2.00-2.5	0.10 Max						
1.00	16.0-18.0	12.00-16.0	2.00-3.0							
1.00	16.0-18.0	11.00-14.0	2.00-3.0							
0.75	16.0-18.0	12.00-14.0	2.00-2.5							
0.75	16.0-18.0	11.00-14.0	2.00-3.0							
0.75	16.0-18.0	10.00-14.0	2.00-3.0	0.10 Max.		5(C+N)-0.70				
1.00	16.5-18.5	10.50-13.5	2.00-2.5			5XC TO 0.70				
1.00	16.0-18.0	10.00-14.0	2.00-3.0			5XC Min.				
1.00	17.0-19.0	9.00-12.0				5(C+N)-0.70				
1.00	17.0-19.0	9.00-12.0				5XC TO 0.70				
1.00	17.0-19.0	9.00-13.0				5XC Min.				
1.00	17.0-19.0	9.00-12.0				5(C+N)-0.70				
1.00	17.0-19.0	9.00-12.0				5XC - 0.80				
0.75	17.0-20.0	9.00-13.0				4XC - 0.60				
1.00	17.0-20.0	9.00-13.0			10XC-1.10					0.0015 - 0.00050
1.00	17.0-19.0	9.00-12.0			10XC - 1.0					
1.00	17.0-19.0	9.00-13.0			10XC Min.					
1.00	17.0-19.0	9.00-13.0		0.10 Max.	5XC-1.10					
1.00	17.0-19.0	9.00-12.0			10XC - 1.2					
1.00	17.0-19.0	9.00-13.0			8XC-1.00			0.10-0.30		
1.00	11.5-14.5	0.50(MAX)						0.10-0.30		
1.00	12.0-14.0									
1.00	11.5-13.5									
1.00	11.5-13.5	0.75								
1.00	16.0-18.0									
1.00	16.0-18.0									
1.00	21.0-23.0	4.50-6.50	2.50-3.5	0.08-0.20						
1.00	21.0-23.0	4.50-6.50	3.00-3.5	0.14-0.20						
1.00	21.0-23.0	4.50-6.50	2.50-3.5	0.10-0.22						
0.90	24.0-26.0	6.00-8.0	3.00-5.0	0.24-0.30			0.50 Max.			
1.00	24.0-26.0	6.00-8.0	3.00-4.5	0.24-0.35						
1.00	24.0-26.0	6.00-8.0	3.00-4.0	0.20-0.30			0.50-0.10		0.50-1.00	
1.00	24.0-26.0	6.00-8.0	3.00-4.0	0.20-0.30				0.50-1.00		



Mechanical Properties Of Stainless Steel

MECHANICAL PROPERTIES				
	Tensile Strength	Yield Strength	Elongation %	Hardness
Grade	Min. Ksi (Mpa)	Min. Ksi (Mpa)	GL : 50 mm MIN	HRB MAX
TP 304	75 (515)	30 (205)	35	90
TP 304H	75 (515)	30 (205)	35	90
TP 304L	70 (485)	25 (170)	35	90
TP 316	75 (515)	30 (205)	35	90
TP 316H	75 (515)	30 (205)	35	90
TP 316L	70 (485)	30 (170)	35	90
TP 316Ti	75 (515)	30 (205)	35	90
TP 309S	75 (515)	30 (205)	35	90
TP 310S	75 (515)	30 (205)	35	90
TP 317	75 (515)	30 (205)	35	90
TP 317L	75 (515)	30 (205)	35	90
TP 321	75 (515)	30 (205)	35	90
TP 347	75 (515)	30 (205)	35	90
TP 405	60 (415)	30 (205)	20	95
TP 409	55 (380)	25 (170)	20	95
TP 410	60 (415)	25 (205)	20	95
TP 430	60 (415)	35 (240)	-	90
TP 904L	71 (490)	31 (215)	35	90
1.4301	(500-700)	(195)	40	-
1.4307	(460-680)	(180)	40	-
1.4401	(510-710)	(205)	40	-
1.4404	(490-690)	(190)	40	-
1.4541	(500-730)	(180)	35	-
1.4571	(500-730)	(210)	35	-
1.4462	(640-880)	(450)	22	-
UNS S31803	90 (620)	65 (450)	25	30 HRC
UNS S32750	116 (800)	80 (550)	15	32 HRC
UNS S32205	95 (655)	70 (-485)	25	30 HRC



Specifications

ASTM Specification Stainless Steel Pipes

A312/A312M	Specification For Seamless And Welded Austenitic Stainless Steel Pipe
A333 /A333M	Specification for Seamless and Welded Steel Pipe for Low-temperature Service
A358/A358M	Specification For Electric-fusion-welded Austenitic Chromium-nickel Alloy Steel Pipe For High-temperature Service
A530/A530M	Specification For General Requirements For Specialized Carbon And Alloy Steel Pipe
A790/A790M	Specification For Seamless And Welded Ferritic/austenitic Stainless Steel Pipe
A928/A928M	Specification For Ferritic/austenitic (duplex) Stainless Steel Pipe Electric Fusion Welded With Addition Of Filler Metal
A999M	Specification For General Requirements For Alloy And Stainless Steel Pipe

ASTM Specification Stainless Steel Tubes

A213/A213M	Specification For Seamless Ferritic And Austenitic Alloy-steel Boiler, Super Heater, And Heat-exchanger Tubes
A249/A249M	Specification For Welded Austenitic Steel Boiler, Superheater, Heat-exchanger, And Condenser Tubes
A268/A268M	Specification For Seamless And Welded Ferritic And Martensitic Stainless Steel Tubing For General Service
A269	Specification For Seamless And Welded Austenitic Stainless Steel Tubing For General Service
A270	Specification For Seamless And Welded Austenitic Stainless Steel Sanitary Tubing
A334/A334M	Specification For Seamless And Welded Carbon And Alloy-steel Tubes For Low-temperature Service
A450/A450M	Specification For General Requirements For Carbon, Ferritic Alloy, And Austenitic Alloy Steel Tubes
A688/A688M	Specification For Welded Austenitic Stainless Steel Feed Water Heater Tubes
A778 - A778	Specification For Welded, Un Annealed Austenitic Stainless Steel Tubular Products
A789/A789M	Specification For Seamless And Welded Ferritic/austenitic Stainless Steel Tubing For General Service
A1016	Standard Specification For General Requirements For Ferritic Alloy Steel, Austenitic Alloy Steel, And Stainless Steel Tubes

ASTM Specification Mechanical Tubing

A511	Specification For Seamless Stainless Steel Mechanical Tubing
A554	Specification For Welded Stainless Steel Mechanical Tubing

EN Standards

DIN EN 10216-5	Seamless Steel Tubes For Pressure Purposes
DIN EN 10217-7	Welded Steel Tubes For Pressure Purposes
DIN EN 10297-2	Seamless Steel Tubes For Mechanical And General Engineering Purpose
DIN EN 10305-1	Steel Tubes For Precision Application

German Standards

DIN 11850	Stainless Steel Tubes For Food And Chemical Industries
DIN 17455	General Purpose Welded Circular Stainless Steel Tubes
DIN 17456	General Purpose Seamless Circular Stainless Steel Tubes
DIN 17457	Welded Circular Austenitic Stainless Tubes Subject To Special Requirement
DIN 17458	Seamless Circular Austenitic Stainless Tubes Subject To Special Requirement
DIN 28180	Seamless Steel Tubes For Heat Exchanger
DIN 11850	Welded Tubes And Pipes For Food, Beverages, Chemical & Pharmaceuticals Industry

German Standards

GOST 9941	Seamless And Warm-deformed Tubes Made From Corrosion-resistant Steel
-----------	--

Tolerance Chart

ASTM A-270/A1016

(Seamless and Welded Austenitic and Ferritic/) Austenitic Stainless Steel Sanitary Tubing

OUTSIDE DIAMETER (mm)			
[25] and under		+0.13, -0.13	+12.5%, -12.5%
Over [25] to 2 [50]		+0.20, -0.20	+12.5%, -12.5%
Over [50] to 3 [75]		+0.25, -0.25	+12.5%, -12.5%
Over 3 [75] to 4 [100]		+0.38, -0.38	+12.5%, -12.5%
[100] to 5.12 [140], excl.		+0.38, -0.38	+12.5%, -12.5%
[140] to 8 [200], excl.		+0.75, -0.75	+12.5%, -12.5%
8 [200] to 12 [300]		+1.25, -1.25	+12.5%, -12.5%

ASTM A-249/A1016

(Welded, Austenitic Steel Boiler, Superheater, Heat-Exchanger and Condenser Tubes)

Under 1 [25]		+0.1, -0.11	+10.0%, -10.0%
1 to 1.1/2 [25 to 40], incl		+0.15, -0.15	+10.0%, -10.0%
Over 1.1/2 to 2 [40 to 50], excl		+0.2, -0.20	+10.0%, -10.0%
2 to 2.1/2 [50 to 65], excl		+0.25, -0.25	+10.0%, -10.0%
2.1/2 to 3 [65 to 75], excl		+0.30, -0.30	+10.0%, -10.0%
3 to 4 [75 to 100], incl		+0.38, -0.38	+10.0%, -10.0%
Over 4 to 7.1/2 [100 to 200], incl		+0.38, -0.64	+10.0%, -10.0%
Over 7.1/2 to 9 [200 to 225], incl		+0.38, -1.14	+10.0%, -10.0%

ASTM A-312/A999

(Seamless, Welded, and Heavily Cold Worked Austenitic Stainless Steel Pipes)

1/8-1.1/2, incl		+0.40, -0.40	-
Over 1.1/2 to 4, incl		+0.80, -0.80	-
Over 4 to 8, incl		+1.60, -0.80	-
Over 8 to 18, incl		+2.40, -0.80	-
Over 18 to 26, incl		+3.20, -0.80	-
Over 26 to 34, incl		+4.0, -0.80	-
Over 34 to 48, incl		+4.80, -0.80	+20.0, -12.5%
"1/8 to 2.1/2 incl., all t/D ratios"		-	+22.5, -12.5%
"3 to 18 incl., t/D up to 5 % incl."		-	+15.0, -12.5%
3 to 18 incl., t/D > 5%		-	+17.5, -12.5%
"20 and larger, welded, all t/D ratios"		-	+22.5, -12.5%
20 and larger, seamless, t/D up to 5 % incl.		-	+15.0, -12.5%
"20 and larger, seamless, t/D > 5 %"		-	-

ASTM A-269 /A 1016

(Seamless and Welded Austenitic Stainless Steel Tubing for General Service)

Up to 1/2 [13]		+0.13, -0.13	+15.0%, -15.0%
"1/2 to 1.1/2 [13 to 38], excl"		+0.13, -0.13	+10.0%, -10.0%
"1.1/2 to 3.1/2 [38 to 89], excl"		+0.25, -0.25	+10.0%, -10.0%
"3.1/2 to 5.1/2 [89 to 140], excl"		+0.38, -0.38	+10.0%, -10.0%
"5.1/2 to 8 [140 to 203], excl"		+0.76, -0.76	+10.0%, -10.0%
"8 to 12 [203 to 305], excl"		+1.01, -1.01	+10.0%, -10.0%
"12 to 14 [305 to 356], excl"		+1.26, -1.26	+10.0%, -10.0%

ASTM A-213/A1016

(Seamless Ferritic and Austenitic Alloy-Steel Boiler, Superheater, and Heat-Exchanger Tubes)

Under 1 [25]		+0.1, -0.11	+20%, -0.0%
1 to 1.1/2 [25 to 40], incl		+0.15, -0.15	+20%, -0.0%
Over 1.1/2 to 2 [40 to 50], excl		+0.2, -0.20	+20%, -0.0%
2 to 2.1/2 [50 to 65], excl		+0.25, -0.25	+20%, -0.0%
2.1/2 to 3 [65 to 75], excl		+0.30, -0.30	+20%, -0.0%
3 to 4 [75 to 100], incl		+0.38, -0.38	+20%, -0.0%
Over 4 to 7.1/2 [100 to 200], incl		+0.38, -0.64	+20%, -0.0%
Over 7.1/2 to 9 [200 to 225], incl		+0.38, -1.14	+20%, -0.0%

Permissible variations from the specified average wall thickness shall be $\pm 10\%$ of the specified average wall thickness for cold formed tubes

ASTM A-268/A789

(Seamless and Welded Ferritic and Martensitic Stainless Steel Tubing for General Service)

Up to 1/2 [12.7], excl		+0.13, -0.13	+15.0%, -15.0%
1/2 to 1.1/2 [12.7 to 38.1], excl		+0.13, -0.13	+10.0%, -10.0%
1.1/2 to 3.1/2 [38.1 to 88.9], excl		+0.25, -0.25	+10.0%, -10.0%
"3.1/2 to 5.1/2 [88.9 to 139.7], excl"		+0.38, -0.38	+10.0%, -10.0%
"5.1/2 to 8 [139.7 to 203.2], incl"		+0.76, -0.76	+10.0%, -10.0%

Quality Policy

Ratnatech is dedicated to Produce World class tubular products by implementing innovative technologies-skilled workmanship and ensuring ample resources in every aspect.

We are equally dedicated to meeting customer needs and expectations by actively engaging all employees at each level and cultivating a sense of pride among them.

Ratnatech sources all its raw materials from authorized high-quality suppliers, adhering to approved manufacturing and inspection plans for quality. Additionally, incoming materials undergo rigorous quality testing upon receipt.

The quality control division oversees and ensures quality assurance from the stage raw material to finishing to meet customer as well as standard specifications.

Two types of Quality Testing Process We Follow

Destructive Testing


- Tensile Test
- Hardness Test
- Flattening Test
- Flaring/Drift Expanding Test
- Flange Test
- Reverse-Bend Test
- IGC Test - Practice A,B,C & E
- Reverse - Flattening Test
- "U" Bend Mock Up test
- Residual Stress Measurement
- Spectro Test

Non Destructive Testing

- Hydrostatic Test
- Eddy Current Test
- Ultrasonic Test
- Air Under Water (Pneumatic) Test
- PMI Test
- Dye Penetrant Test
- Boroscopic (ID Camera) Test
- ID Eddy Current Test 7
- Surface Roughness



Quality Testing



Air Under Water (Pneumatic Test)



Tensile Test



PMI Test




Hardness Test




Ultra Sonic Test




IGC Test- Practice A, B, C & E



Reverse-Bend Test



Residual Stress Measurement



Flattening Test



Flattening/Drifting Expanding Test



Muffle Furnace Test



Eddy Current Test



"U" Band Mockup Test



Spectro Test



Dye Penetrant Test



Impact Test

Product Marking

Ratnatech ensures continuous line product marking apart one or two meter on length with full details like LOGO, Make, Size (OD X THK X Length), Specification, Grade, Heat Number, Customer Purchase Order with date, Item Code or any special requirement requested by customer.

Packaging

Ratnatech always ensures importance of customer requirements at each and every stage. Our pipes & tubes are packed as per customer requirements prior to shipment.

We also ensure protective end caps outside or inside as required, fumigation of wooden boxes as well as silica gel inside the boxes on request.



+91 98244 85784, +91 98844 08584

info@ratnatechstahl.com

www.ratnatechstahl.com

Survey No.1521, Village : Rajpur, Ahmedabad-Mehsana Highway, Sub-District : Kadi, District : Mehsana-382715, Gujarat, India.



RATNATECH
STAHL PVT LTD